




PCT/NO 04 / 00116



INVESTOR IN PEOPLE

BEST AVAILABLE COPY



The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ


I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

I also certify that the attached copy of the request for grant of a Patent (Form 1/77) bears an amendment, effected by this office, following a request by the applicant and agreed to by the Comptroller-General.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Dated

13 May 2004

PRIORITY  
DOCUMENT  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)



177  
24APR03 E802107-1 D10166  
P01/7700 0.00-0309224.4

**Request for grant of a patent**  
(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road  
Newport  
Gwent NP9 1RH

1. Your reference

EMT 2 115095

2. Patent application number

(The Patent Office will fill in this part)

0309224.4

3. Full name, address and postcode of the or of each applicant (underline all surnames)

EMT Research AS  
Kjolnes ring 56  
N-3918 PORSGRUNN  
NORWAY

Patents ADP number (if you know it)

8616997001

If the applicant is a corporate body, give the country/state of its incorporation

NORWAY

4. Title of the invention

METHOD FOR FLOW IMPROVEMENT AND REDUCTION OF FOULING IN PROCESS EQUIPMENT

5. Name of your agent (if you have one)

ONSAGERS AS

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

c/o Sam Briddes  
John Brown Hydrocarbons Limited  
20 Eastbourne Terrace  
London W2 6LE  
C/o Norwegian Trade Council  
5 Lower Regent Street  
LONDON  
SW1Y 4LR

Patents ADP number (if you know it)

8273419007

08776296001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number  
(if you know it)

Date of filing

(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing

(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
- b) there is an inventor who is not named as an applicant, or
- c) any named applicant is a corporate body.

YES

See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form.  
Do not count copies of the same document

Continuation sheets of this form nil

Description 10

Claim(s) 2

Abstract one

Drawing(s) 8 — 2

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*) one

Request for preliminary examination and search (*Patents Form 9/77*) one

Request for substantive examination  
(*Patents Form 10/77*)

Any other documents  
(please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature

Date 2003 APR 23

Sam Briddes - Chartered Patent Agent

12. Name and daytime telephone number of person to contact in the United Kingdom SAM BRIDDES 0207 957 3626

**Warning**

*After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.*

**Notes**

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

Method for flow improvement and reduction of fouling in process equipment

**Technical field**

This invention relates to a method and apparatus for improvement of flow rates and reduction of fouling in process equipment such as for instance heat exchangers where fluids are flowing in single or multiphase. An improved flow rate will cause that the heat exchanger becomes more efficient, i.e. a lower deposition rate and a higher removal rate of inorganic agents. The fluid may be a pure fluid, colloidal fluid or contain inclusions in the form of particles.

**Background**

The formation of deposits (foulants) on heat transfer surfaces is a major cost factor in the installation and operation of heat exchangers. The accumulation of deposits on the heat transfer surfaces often results in reduced heat transfer rates and may cause other problems of operation. Heat exchangers are used in almost all kinds of industries including process industry and oil industry. Consequently, the fouling problem is present in almost all kinds of industries. The total fouling related costs for the industrialized world are estimated to be in the order of 40,000 million dollar U.S. per year [1].

Despite the enormous costs associated with fouling, only very limited research has been done on this subject. Reliable knowledge of fouling economics is important when evaluating the cost efficiency of various mitigation strategies. Despite the great practical experience with fouling preventing methods, and the results from ongoing research, the fouling in heat exchangers is still a great problem. Therefore, there is a great need for development of new and more effective methods to reduce or prevent the rate of fouling in heat exchangers [1].

**Prior art**

There are known several chemical and physical/mechanical methods for reducing/-removing the scaling and/or fouling problem in systems where water and/or other process liquids are flowing. However, their efficiencies vary a lot from method to method, and they also suffer some disadvantages.

One widely known and long used approach to handle the problem with scaling and/or fouling in heat exchangers is the so-called chemical methods where one or several agents is(are) added to the liquid(s) in the system in order to increase the solubility of the compounds that forms the scaling and/or fouling. These methods are known to be effective in both preventing formation of scaling/fouling and to dissolve already formed scaling/fouling. In the case of heat exchangers, it is common to either add the agent(s) to the process fluid, which often reduce the quality of the produced products, or to the cooling/ heating medium which may represent a pollution problem. These problems can be solved by performing

periodic cleansing procedures where the heat exchanger is disconnected from the process line and flushed with a cleansing liquid. But in this case, the normal operation of the process must obviously be stopped with attendant increased operating costs. As a result, chemical treatments are often found to expensive and labour demanding to be an acceptable solution to the problem with scaling/fouling.

It has therefore been an increased focus on preventing, and in some cases even reversing scale formation by applying an electric and/or magnetic field to the flowing water and/or process liquid. It is generally assumed that the cause of this effect is that exposing the water/liquid flow to electromagnetic fields may generate nuclear clusters in the bulk liquid that act as seed crystals, such that the scale- and/or fouling forming compounds are precipitated as solid suspended particles in the bulk liquid and then carried along with the bulk stream. An example of such technology is disclosed in EP 0720588, where water is subject to radiofrequency signals in order to prevent scale formation. It has also been reported that magnetic fields may be useful for preventing lime scaling in much the same manner as electric fields. An example of such technology is disclosed in US 4 278 549. In WO 94/02422 it is described a device and method where the water flow is exposed to microwave radiation which frequency is tuned to be absorbed by one or several of the following ions/compounds of the water:  $\text{Ca}^{2+}$ ,  $\text{CO}_3^{2-}$ ,  $\text{HCO}_3^-$ ,  $\text{CO}_2$ ,  $\text{CaHCO}_3^+$ ,  $\text{H}_2\text{CO}_3$ , and  $\text{H}_2\text{O}$ . It is believed that the electromagnetic radiation causes the precipitates to be form on a micro-scale in the bulk flow to be carried away instead of on the surfaces of the process equipment.

In the case of scaling, or build up of precipitated  $\text{CaCO}_3$ , the effect of such electromagnetic treatment methods is thoroughly discussed by American Petroleum Institute [2] and scientists [3-10]. The results obtained from various experiments and tests are controversial. Some results show that the magnetic and/or electric fields reduce precipitation of calcium carbonate, others do not. However, the way the magnetic/electric fields are introduced, and the magnitude of the fields vary from experiment to experiment. Consequently, the parameters that describe the exposure system also vary from experiment to experiment. In addition, no quantitative relationship between the parameters that describe the magnetic/electric fields and the effect on the fluid flow system has been reported. Therefore, by this lack of scientific knowledge, it is almost impossible to fully control of the effect of those methods on deposition of calcium carbonate.

However, theoretical and experimental investigations have been performed to understand the mechanisms of fouling and to reduce the rate of fouling in heat exchangers. The mechanisms include crystallization fouling, particulate fouling, biological fouling, chemical reaction fouling, corrosion fouling, and freezing fouling. However, it is unlikely that fouling is exclusively due to a single mechanism, but in many situations, one mechanism will be dominant. Results from

the investigations on the various mechanisms involved in the fouling process have revealed that the following three parameters are of greater significance than others concerning control of the fouling process: the temperature gradient across the heat exchanger surface, the concentration of the foulant, and the flow velocity at the heat exchanger surface [11,12]. The latter effect is exploited in this invention.

#### Objective of the invention

The main objective of this invention is to provide a method and apparatus for improving/enhancing the flow velocity in process equipment where a process liquid is flowing in order to reduce/eliminate the problem with fouling.

Another objective of this invention is to provide a method and apparatus for improving/enhancing the flow velocities at the heat transfer surfaces in heat exchangers in order to increase the efficiency of the heat exchangers and at the same time reduce/eliminate the problem of fouling.

#### Summary of the invention

The objectives of this invention are obtained by the method and apparatus as defined in the appended claims and/or the following description of the invention.

The present invention is partly based on an effect that was discovered by the present inventor, and which formed basis for another invention that is protected by for example US 6 334 957 or the corresponding EP 1 021 376. This patent family gives a thorough description of the effect, and is therefore included by reference in this application. Here, it will only be given a short summary of the effect:

- When a fluid flows through a pipe, there will be torn loose electric charges at the wall of the pipe due to shear forces in the boundary layer. This will give rise to an electric potential (the electric friction potential) at the pipe wall that will attract and retain charged particles, ions and dipoles in the fluid, and thus induce a friction force that reduces the flow velocity of the liquid in the pipe. This contribution the flow friction is often referred to as the electric contribution to the friction factor.

The invention disclosed in US 6 334 957 is based on that this build-up of electric charges at the fluid-solid boundary can be counteracted by imposing a DC electric potential on the pipe/duct wall that exactly balances the build-up of electrical charges on the wall. Then the electromagnetic force that attracted the ions and polar molecules will diminish, and the ions and polar molecules may freely follow the flowing fluid. In other words, the electrical contribution to the friction factor becomes zero, and the average flow velocity of the fluid will consequently increase, especially at the liquid-solid boundary (at the wall). US 6 334 957 discloses a

G

regulation method that ensures that the imposed DC potential exactly opposes the electric friction potential at all times and an apparatus for performing the method.

5 The present invention is based on the discovery that the elimination of the electric friction factor for liquids flowing in pipes, heat exchangers, reactors and all other forms of industrial process equipment, is also a convenient and effective mean for preventing and in some cases even revert already formed fouling and scaling. That is, by enhancing the flow velocities at the surfaces of heat exchangers and other process equipment where fluids are flowing, one will reduce the deposition rate of precipitates thus reduce/prevent formation of scales, fouling, and any other types of solid deposits on the walls of the heat exchanger/process equipment. This is 10 believed to be due to that the enhanced flow velocity at the solid-liquid boundary (the heat exchanger wall) will carry away a larger portion of the solid precipitates in the bulk stream.

15 It is surprising that the effect of the modest increases of the flow velocities that are being obtained by removing the electric contribution to the flow friction factor is able to give an effective reduction of the deposition rate of precipitates such that the invention becomes an efficient tool for handling the problem of scaling/fouling in heat exchangers and other process equipment. Not to say that these modest velocity increases, usually in the order of 1-10%, are also able to increase the shearing action at the deposit-fluid interface sufficiently to remove already formed deposits. 20

This surprising finding gives a substantial benefit over prior art methods which exploits electromagnetic fields/potentials to prevent fouling/scaling, since the prior methods are focused on that the electromagnetic fields/potentials must be sufficiently strong and act on the bulk liquid in order to enhance the nuclear 25 clustering and precipitation of the scale and/or foulant forming compounds in the process liquid such that the precipitates will be carried away with the bulk flow. But in this case, one will inevitably alter the chemical conditions in the process fluid and may ionise one or more of the liquid compounds or electrically induce one or more electrochemical reactions in the process fluids. Thus, the prior art should be used with care in process industry in order not to induce detrimental side effects in 30 the process. Another unwanted side-effect of these prior art methods is that the employed electromagnetic fields/potentials are almost certain to be of a different magnitude than the electric friction potential, such that the imposed potential will almost certain create a new electric friction potential that may very well be larger than the natural occurring friction potential. This will then slow the flow velocity, 35 which enhances the deposition rate of precipitates. This may be one explanation of why many prior art methods are encumbered with instability.

In the present invention, the imposed electric potential shall exactly counter-balance the natural occurring electric friction potential of the flow. Thus these potentials

will cancel each other such that no electric fields will be felt by the process liquid. Consequently, there will be no risk of inducing any electrochemically alterations of the processes in the flowing process fluid, including alterations of chemical equilibriums, ionising compounds, creating radicals, induce unwanted chemical reactions etc. The naturally occurring electric friction potentials are usually small, in the order plus/minus a few Volts or less, such that one can manage with much less powerful and thus energy efficient fields than in prior art methods. The method according to the invention will therefore be absolutely risk free, both in terms of electrochemistry and handling safety, such that it becomes suited for all thinkable processes, no matter which process liquid that flows through the process equipment.

Another benefit over prior art is that the invention is based on scientific knowledge, such that the method according to the invention will be fully controllable and give consistent results. A further advantage is that the invention represents no pollution problem since no matter is added or removed when implementing the invention and no chemical reactions are induced in the process fluids that may cause unwanted detrimental effects on the process and/or the environment.

In the case of process liquids containing chemically active components, there will normally be another naturally occurring potential that must be taken into account. When a metal (e.g. heat transfer surface) is immersed in a solution (fluid), an electrical potential between the surface of the metal and the solution is established, i.e. the surface is electrified. Most of the metals will normally be negatively charged, and the electrical potential can be measured in relation to a reference cell (e.g. a standard calomel reference cell, SCE). The potential is named the corrosion potential. If the surface is electrified, an additional adhesion appears which is caused by the attractive forces between electrical charges on the surface and the counter-ions or/and dipole molecules in the fluid [13]. This phenomenon represents an additional contribution to the electric friction factor for the fluid flow at the heat transfer surface, which also should be countered by the imposed DC-field. Thus, in this application; the term electric contribution factor means the combined effect of the corrosion potential and the fluid flow friction potential on the total friction factor for the fluid flow.

The invention is related to all kinds of heat exchangers (HE), including air-cooled HE, plate and frame HE, compact HE, shell and tube HE, double-pipe HE, spiral HE, shell-and tube condensers, air-cooled condensers, plate and compact condensers, direct contact condensers, cooling towers, steam generators, boilers, and evaporators. The invention is also related to either the process fluid side or cooling/heating medium side of the heat transfer surface, or both. Also, all other types of industrial and non-industrial process equipment where process liquids are flowing and where scaling/fouling may pose a problem are included.



Thus is summary; the inventive idea is to employ a DC electric potential that exactly counteracts the combined build-up of an electric potential due to the friction from the flowing fluid and the corrosion potential. Thus the electrical potential across the boundary layer (at the liquid-wall interface) is reduced to zero such that the electric contribution to the fluid flow friction at the surface is reduced to zero, and consequently, a maximum increase in the flow rate near the surface will be achieved, which again leads to a reduction/elimination of the deposition rate of suspended precipitates. The naturally occurring potentials at the liquid-solid interface will be less than  $\pm 5$  V, but typically less than  $\pm 2.5$  V, and often in the order of  $\pm 1.0$  V or less.

In order to put the inventive idea into practice, the inventive method may be implemented in a device comprising a control unit which ensures that the imposed DC-potential exactly counters the naturally occurring potential at the liquid-solid boundary. The control unit comprises three parts: a measuring/calculator unit, an electrical DC-potential generator, and a regulator. These components are of conventional nature and need no further description. A similar system is thoroughly described in US 6 334 957 or the corresponding EP 1 021 376. The regulation unit calculates the magnitude of the imposed DC-potential due to information of measured fluid properties upstream of the part of the pipe/duct that is exposed to the DC field, and where that the measured fluid properties may be one or more of the properties contained in the group comprising average flow velocity, corrosion potential, pH, concentration of specific ions contained in the fluid, electrical conductivity, pressure, and temperature.

#### Detailed description of the invention

The invention will now be described in more detail under reference to a preferred embodiment of the invention.

A preferred embodiment of the invention, when implemented on a shell and tube heat exchanger of is shown schematically in Figure 1. The arrows indicate the flow directions. The invention 1 is connected to the heat exchanger 2 by two or more connectors of conventional type (not shown in the Figure). One connector is connected to a ring 4 in the inlet for the cooling/heating medium 3 which is electrically insulated from the rest of the system. One connector is connected to a ring 7 in the inlet for the process fluid 6 which is also electrically insulated from the rest of the system. A third connector is connected to the heat exchanger itself at the point marked 9. If the invention is used for flow improvement of the process fluid, the connecting point 9 will be at the outlet for the process fluid 5. For the improvement of the cooling/heating medium flow, the connecting point 9 will be at outlet 8. For the flow improvement of the cooling/heating medium, ring 4 is used, and for the process fluid, ring 7 is used.

When the invention is switch into measuring/calculator mode, the set point for the regulator is determined, as described in the following:

The estimation of the set point is based on capacitance measurements. The capacitance is measured between the ring 4, or 7, and the heat exchanger 9 itself by the alternating current method, as a function of the applied DC-potential. Its positive and negative ends are connected to 9 and 4, or 7, respectively. The potential at which the capacitance shows a minimum value, corresponds to the un-electrified condition of the heat exchanger, and is the particular DC-potential used as set point for the regulator. When the invention is switch into working mode, the electrical DC-generator applies the potential between 4, or 7, and 9, and is controlled by the regulator.

#### Verification of the invention

In order to verify the ability of the invention to reduce deposition of precipitates, a colloid solution of calcium carbonate and barium sulphate in flowing water were made and experiments performed to investigate the deposition rates on a titanium surface. The calcium carbonate and barium sulphate is dispersed (colloid state) in the flowing fluid passing the titanium plate.

#### EXPERIMENTAL

##### Solutions

Preparation of the colloid solution of calcium carbonate and barium sulphate: 1 l of 0.00025 M  $\text{BaCl}_2$  and 1 l of 0.00025 M  $\text{CaCl}_2$  is mixed, and then 2.5 ml of 1 M  $\text{Na}_2\text{CO}_3$  is added. Finally, 25 ml of 0.01 M  $\text{Na}_2\text{SO}_4$  is added. In this way a colloid solution of calcium carbonate and barium sulphate is obtained. For fresh solution and room temperature, light scattering measurements performed at different wavelengths give the size calcium carbonate and barium sulphate particles equal to about 50 nanometres. In two-three days these particles reach the size of about 100 nm. Further growth of the size leads to the transformation of the colloid into suspension and the precipitation of calcium carbonate and barium sulphate is observed. Then the colloid solution is replaced by newly prepared solution.

During the experiments carried out at  $38^\circ\text{C}$ , the growth of the size of the particles and the precipitation was much faster. Therefore, every day a new solution has been used.

During the measurements, the content of calcium and barium was controlled by atomic absorption spectroscopy.

##### Flow system

Schematic representation of liquid flow system is presented in Fig. 2. The tube is in the loop which contains two reservoirs with simulated fluid and the peristaltic pump (P). The flow velocity is controlled by the height (H), while the temperature of

liquid is controlled by a thermo reservoir 2. This reservoir also serves for avoiding the periodic pressure changes which arise during the work of the peristaltic pump and which can influence the frequency of quartz crystal oscillation.

### Electrodes and Instrumentation

5 The 5 MHz AT-cut 15 mm diameter and 0.3 mm thick quartz crystals were used. Both sides of crystals were coated with titanium by cathodic sputtering. The decrease in frequency change is linearly related with an increase of electrode mass. The fundamental frequency of quartz crystal (5 MHz) and the geometric area of a circular titanium region in the centre of the crystal ( $0.2 \text{ cm}^2$ ) give the EQCM mass  
10 sensitivity equal to  $25 \cdot 10^{-9} \text{ g Hz}^{-1} \text{ cm}^{-2} = 25 \text{ ng Hz}^{-1} \text{ cm}^{-2}$ . These coated working quartz crystals (QCM1, QCM2 and QCM3, see Figs. 3 and 4) were glued into cylindrical holders, which were affixed to the tube in three different ways, see Fig. 3. One side of the crystals were exposed to the solution in the tube and served as working electrodes (QCM1, QCM2 and QCM3, see Figs. 3 and 4). Another side of  
15 these crystals faced the air.

The working quartz electrodes were inserted into three separately controlled oscillators - QCM drivers (Fig. 4) configuration of which allows the working electrodes to be grounded. Home-made voltammetric and frequency measurement system was used (Fig. 4). In this system, a high precision frequency counter  
20 performs a measurement with accuracy in 0.1-0.2 Hz for about 5 MHz frequency in 3 ms.

During the measurements, the same potential was applied simultaneously to all three electrodes and the changes of the frequency of these quartz supported electrodes with time were separately recorded for 600 s. Then the same experiment  
25 was repeated for another potential. In such a way, the potential range from 1 V to -1 V vs. the standard hydrogen electrode (from 0.8 V to -1.2 V vs. the silver/silver chloride/saturated KCl electrode) with 0.1 V increments was investigated.

### Results

30 1. Measurements in colloid solution at flow rate 3 l/min ( $Re=1300$ ) and room temperature ( $22^\circ\text{C}$ )

The results of these measurements are depicted in Figs. 5-9.

Low rates observed in fresh colloid solution at the most positive potentials (Fig. 5) can be explained by very small size of the particles (less than 50 nm). During the  
35 measurements they were growing (growing was followed by the light scattering technique). That could be the reason for the rate growth when the potential is changed in negative direction but still remains in positive region. When the experiments were repeated next day and on the third day in the same solution, in

positive region the potential influence on the mass deposition rate is smaller (Figs. 8 and 9).

In the negative potential region, the clear potential influence is observed - mass deposition rate is noticeably decreased (Figs. 5, 8 and 9)

- 5 Fig. 8 - the same solution and the same conditions of the measurements as given in Fig. 5 but the measurements were performed the next day after the experiments, the results of which are presented in Fig 7. The size of particles is approximately 100 nm and still growing, though much slower. The data presented in Fig. 8 show the influence of the potential (growth effects are small). Fig. 9 - solution turned to be more opalescent, the size of particles is larger than 100 nm and solution turned to be more opalescent (white colour of the solution is visually observed).
- 10

- The rates of mass deposition onto these electrodes were very small and similar for the first two days (Figs. 6 and 7). The measurements, repeated on the third day (the data for bottom electrode are presented in Fig. 9) revealed some similarity to the behaviour of bottom electrode, though the absolute values of the rates are noticeably smaller.
- 15

## 2. Measurements in colloid solution at increased flow rate 4 l/min ( $Re=1700$ ) and room temperature ( $22^{\circ}C$ )

- 20 The results of these measurements are depicted in Figs. 10-12.

Decrease in deposition rates, observed at higher flow rates (Figs. 10 and 11), may be related with "washing" of particles from the electrode surface.

- Both experiments 1 and 2 are carried out at laminar flow (the Reynolds numbers are 1300 and 1700, respectively). At laminar flow, the friction factor decreases with increasing Reynolds number. The decrease in deposition rates, observed at higher flow rates (Figs. 9 and 10), may be related with lower friction factor.
- 25

### Conclusion

- The results show that the deposition rate of calcium carbonate and barium sulphate on an electrode surface depends on the applied electrical DC-potential within the range of 0.8 - 1.0 V (Ag/AgCl<sub>2</sub> reference electrode). Within certain ranges a decrease in the deposition rate is observed, while an increase is observed in other ranges.
- 30

The results show that the deposition rate decreases with higher flow rates, which indicates that the effect, maybe, is related with lower friction factor.

## References

- 1) Müller-Steinhagen, H. (2000). Heat Transfer Fouling. Localized 14.02.03:  
<http://www.cpe.surrey.ac.uk/dptri/hms/fouling.htm>
- 5 2) Evaluation of the principles of magnetic water treatment, American  
Petroleum Institute, Washington DC, 1985. (API Publication 960).
- 3) Gamayunov, N.I. Enlargement of particles in water streams under the  
influence of crossed electric and magnetic fields. J.Appl.Chem., 57, 1984.
- 10 4) Baker, J.S., Judd, S.J. Magnetic amelioration of scale prevention. Wat.Res.,  
30, 1996.
- 5) Parsons, S.A., Wang, B.L., Judd, S.J., Stephenson. T. Magnetic treatment  
of calcium carbonate scale-effect of pH control. Wat.Res., 31, 1997.
- 6) Quinn, C.J. Magnetic treatment of water prevents mineral build-up. Iron  
and Steel Engineer, 74, 1997.
- 15 7) Barrett, R.A., Parsons, S.A. The influence of magnetic fields on calcium  
carbonate precipitation. Wat.Res., 32, 1998.
- 8) Coey, J.M.D, Cass, S. Magnetic water treatment. J.Magn.Magn.Mater., 209,  
2000.
- 20 9) Gabrielli, C., Jaouhari, R., Keddami, M. Magnetic water treatment for scale  
prevention. Wat.Res., 35, 2001.
- 10) Kobe, S., Drazic, G., McGuinness, P.J., Strazisar, J. The influence of the  
magnetic field on the crystallization form of calcium carbonate and the  
testing of a magnetic water-treatment device. J.Magn.Magn.Mater., 236,  
2001.
- 25 11) Hewitt, G.F., Shires, G.L., Bott, T.R. Process heat transfer. CRC Press,  
Boca Raton, 1994.
- 12) Hasson, D., Bramson, D. Effectiveness of magnetic water treatment in  
suppressing  $\text{CaCO}_3$  scale deposition. Ind.Eng.Chem.Process Des. Dev., 24,  
1985.
- 30 13) Bockris, J.O.M., Reddy, A.K.N. Modern electrochemistry, vol. 2A, 2<sup>nd</sup> Ed.,  
New York, Kluwer Academic/Plenum Publishers, 2000.

## CLAIMS

1. A method for reducing fouling and/or scaling in process equipment containing flowing fluids, by imposing a direct current (DC) electric potential on the wall of the pipe/duct in order to remove the electric contribution to the friction factor, where the imposed DC electric potential is regulated by a regulating unit which is fed with information of measured fluid properties, characterised in that the imposed DC electric potential is constantly regulated such that the imposed DC-potential has the exact same strength but with opposed polarity as the naturally occurring potential due to build-up of electrical charges on the wall from the interaction between the flowing fluid and wall material.
2. A method according to claim 1, characterised in that the regulating unit is fed with information of measured fluid properties upstream of the part of the pipe/duct that is exposed to the DC field, and that the measured fluid properties may be one or more of the properties contained in the group comprising average flow velocity, corrosion potential, pH, concentration of specific ions contained in the fluid, electrical conductivity, pressure, and temperature.
3. A method according to claim 1 or 2, characterised in that the DC electric potential is in the range of -5.0 to +5.0 V (saturated calomel electrode, SCE).
4. A method according to claims 1 - 3, characterised in that the DC electric potential is in the range of -2.5 to +2.5 V (saturated calomel electrode, SCE).
5. A method according to claims 1 - 3, characterised in that the DC electric potential is in the range of -1.0 to +1.0 V (saturated calomel electrode, SCE) or less.
6. A method according to claims 1 - 5, characterised in that the flow is a streaming pure fluid in gas or liquid state, a colloidal fluid, a fluid which contains inclusions in the form of particles, a mixture of several fluids, in single or multiphase, or a mixture of one or more of these
7. A method according to claim 1 - 6, characterised in that the flow can have Reynolds numbers in the range 1 to 5 000 000.

8. An apparatus for performing the method given in claims 1-7,  
c h a r a c t e r i s e d i n that a DC electric potential generator is connected  
with one polarity to an electrically insulated part of the pipe/duct wall and the other  
polarity to the part of the pipe that is downstream of the insulated part, and that the  
5 DC electric generator is controlled by a regulating unit which is fed with  
measurements of the fluid properties upstream of the part that is exposed to the DC  
electric potential.
9. An apparatus according to claim 8,  
c h a r a c t e r i s e d i n that the regulating unit is fed with one ore more of the  
10 fluid properties contained in the group comprising average flow velocity, corrosion  
potential, pH, concentration of specific ions contained in the fluid, electrical  
conductivity, pressure, and temperature.
10. A method for reducing fouling and/or scaling in process equipment containing  
flowing fluids, substantially as hereinbefore described by way of example with  
reference to the accompanying drawings.
11. An apparatus for performing the method of any one of claims 1 to 7 and 10,  
substantially as hereinbefore described by way of example with reference to and as  
shown in Figures 1 to 4 of the accompanying drawings

# ABSTRACT


This invention relates to a method and apparatus for improvement of flow rates and reduction of fouling in process equipment such as for instance heat exchangers where fluids are flowing in single or multiphase. This is obtained by imposing a DC-potential at the walls of the process equipment that exactly opposes the naturally occurring potential due to interaction between the walls of the process equipment and the fluid flowing inside.

An improved flow rate will cause that the heat exchanger becomes more efficient, i.e. a lower deposition rate and a higher removal rate of inorganic agents. The fluid may be a pure fluid, colloidal fluid or contain inclusions in the form of particles.



1/8

Figure 1



2/8




Fig. 2 Schematic representation of liquid flow system. The positions of electrodes (QCM1-3) on a tube are shown in Fig. 3.

3/8




Fig. 3. The dimensions of the tube and the positions electrodes: working electrodes QCM1, QCM2 and QCM3, reference electrode and counter electrode (stainless steel).




Fig. 4. Block-diagram of EQCM system

4/8




Fig. 5. The dependence of the mass deposition rate on the potential (bottom electrode) in the fresh solution - calcium carbonate and barium sulphate colloid solution was prepared just before starting measurements (the particles are very small - less than 50 nm, the solution looks clear and transparent).




Fig. 6 The dependence of the mass deposition rate on the potential (top electrode) in the fresh solution - calcium carbonate and barium sulphate colloid solution was prepared just before starting measurements.

5/8




Fig. 7 The dependence of the mass deposition rate on the potential (side electrode) in the fresh solution - calcium carbonate and barium sulphate colloid solution was prepared just before starting measurements.




Fig. 8 The dependence of the mass deposition rate on the potential (bottom electrode) the second day after the calcium carbonate and barium sulphate colloid solution was prepared.

6/8




Fig. 9 The dependence of the mass deposition rate on the potential (bottom electrode) the third day after the calcium carbonate and barium sulphate colloid solution was prepared.

7/8




Fig. 10 The dependence of the mass deposition rate on the potential (bottom electrode) the third day after the calcium carbonate and barium sulphate colloid solution was prepared.




Fig. 11 The dependence of the mass deposition rate on the potential (top electrode) the third day after the calcium carbonate and barium sulphate colloid solution was prepared.

8/8




Fig. 12 The dependence of the mass deposition rate on the potential (side electrode) the third day after the calcium carbonate and barium sulphate colloid solution was prepared.



**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**